

A TWO COMPONENT POLYURETHANE TOPCOAT FOR ACRYLIC, EPOXY AND POLYURETHANE FLOOR SYSTEMS

KEY BENEFIT SUMMARY

- Two component
- Provides high scratch and abrasion resistance
- Resistant to weak solutions of acids, alkalis, salt solutions, fats and oils
- Conductive 10-100 KOhm
- Resistant to petrol and weak solvents

PRODUCT INFORMATION

Description

Hardtop® Conductive is a two component, solvent containing, aliphatic polyurethane based topcoat.

Usage

Hardtop® Conductive is used as a conductive topcoat for epoxy, acrylic or polyurethane floor systems.

Packaging

Prepacked units of 5.56 kg;

Component A: 4 kg resin

Component B: 1.56 kg pigment and conductive parts

Colour: grey.

TECHNICAL INFORMATION

Consistency:	grey viscous
Binder:	polyurethane
Solids:	65%
Drying time at + 20°C:	to touch: 4-5 hours foot traffic: 24 hours wheeled traffic: 48 hours fully cured: 7 days

USAGE GUIDELINES

Surface preparation

The surface to be coated shall be clean and dry. Slight grinding with sandpaper (240) is advisable.

Priming

Not applicable.

Mixing

Good mixing of part A and part B is necessary. If a thin skin is on top of the product, the skin must be completely removed.

Application

Apply with a roller in a thin layer.

Consumption

150 - 200 g/m².

Cleaning

Clean tools with solvent.

STORAGE

Do not store below +5°C. Store in closed container and in dry conditions.

SHELF LIFE

In unopened packaging: 6 months.

HEALTH AND SAFETY PRECAUTIONS

Product- and Safety Data Sheets must be read and understood.

TECHNICAL SERVICE

Contact RPM/Belgium N.V.

GUARANTEE

RPM/Belgium N.V. and Alteco Technik GmbH warrant all goods to be free from defects and will replace materials proven to be defective but make no warranty as to appearance of colour. The information and recommendations herein are believed by RPM/Belgium N.V. and Alteco Technik GmbH to be accurate and reliable.

